



TYPICAL PROPERTIES & SPECIFICATIONS SHEET

conductive containers, inc.

DESCRIPTION: White Dissipative Acrylic Permanent

APPLICATION: Thermoforming
Long Term Use

CCI PART NUMBER: CCI 840

PROPERTY	VALUE (U.S.)	TEST METHOD
Volume Resistivity	$\leq 10^{11}$ Ohms/cm	ESD S11.11
Surface Resistivity	$\leq 10^{11}$ Ohms/sq	ESD S11.11
Surface Resistance	$\leq 10^9$ Ohms	ESD S11.11
Static Decay Rate (1000V-100V)	0.8 Sec	CPM (12% RH)
Static Decay Rate (100V-10V)	2.0 Sec	CPM (12% RH)
Host Polymer	MS-Resin	-----
Filler	IDP	-----
Color	Natural	Visual
Specific Gravity	1.14 g/cc	ASTM D-792
Tensile Modulus	301,000 psi	ASTM D-882
Tensile Strength (Yield)	4,820 psi	ASTM D-882
Tensile Elongation (Break)	19%	ASTM D-882
Flexural Modulus	229,000 psi	ASTM D-790
Heat Deflection Temp @ 66 psi	185 °F	ASTM D-648

CHARACTERISTICS:

- Inherently Static Dissipative
- Humidity insensitive
- Ultra-clean: low off-gassing and low ionic contamination
- Durable
- Available Gauges: .125-.150

APPLICATIONS:

- Medical device packaging
- Electronic component handling
- Hard disk drive component packaging

All values are for pre-formed materials. Electrical values will vary with each individual design.

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Conductive Containers, Inc. as to the effects of such use or the results to be obtained, nor does Conductive Containers, Inc. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.