



TYPICAL PROPERTIES & SPECIFICATIONS SHEET

conductive containers, inc.

DESCRIPTION: Non-permanent Foam
Dissipative Polyurethane

APPLICATION: Short-Term Use

CCI PART NUMBER: ASPU 8800

PROPERTY	VALUE (U.S.)	TEST METHOD
Color	Pink	Visual
Surface Resistance	10 ⁵ -10 ¹² Ohms/sq	ASTM D-257
Static Decay Rate	≤ 2 Sec	FTMS 101-C:4046
Density	1.7-1.9 lbs/ft ³	ASTM D-3574-01
Tensile Strength	10 psi	ASTM D-3574-01
Tensile Elongation	100%	ASTM D-3574-01
Compression Set (50%)	12%	ASTM D-3574-01
Tear Resistance	0.8 lbs/in	ASTM D-3574-01
Indent Force Deflection @ 25%	81-99 psi	ASTM D-3574-01
Flame Resistance	N/A	-----
Shelf Life	Limited	-----

APPLICATIONS:

- Medium weight cushioning



WARNING: FLAMMABLE

Urethane Foam should not be exposed to open flame or other ignition sources. Urethanes burn rapidly with great heat and release gases which are extremely hazardous.

All values are for pre-formed materials. Electrical values will vary with each individual design.

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Conductive Containers, Inc. as to the effects of such use or the results to be obtained, nor does Conductive Containers, Inc. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.