



# LONESTAR ELECTROSTATIC SOLUTIONS

5213 PINWOOD DR. MCKINNEY TEXAS 75071

Phone: 1-770-856-3119

Email: [LonestarESD@outlook.com](mailto:LonestarESD@outlook.com)

Website: [LonestarESD.com](http://LonestarESD.com)

## SUMMARY

Testing of material samples were performed to ANSI/ESD STM11.11 and 11.12 to determine Surface and Volume resistance of the material. A qty of 6 samples were conditioned to the requirements of the test methods. Each was then tested per the referenced test methods with data recorded and shown below. Results showed a range on Surface Resistance of  $10^3$ –  $10^3$  Ohms. Range for Volume Resistance is  $10^3$ –  $10^3$  Ohms.

## MATERIAL:

80PPI Shield 1.2 LB80  
Sample Thickness: 0.125"

## TEST CONDITIONS:

Qty 6 specimens @ 12.8% RH, 23.2°C, 62 hours conditioning.  
Qty 6 specimens @ 50.3% RH, 23.3°C, 55 hours conditioning.  
Test Voltage (@ Upper Resistance): 100 Volts  
Electrification Period (@ Upper Resistance): 8-10 seconds

## TEST DATA

## TEST METHOD/S:

- ANSI/ESD STM11.11-2022
- ANSI/ESD STM11.12-2021

## STANDARDS:

- PROSTAT PRS-801  
RESISTANCE METER (CAL  
DATE 1-2023)
- PROSTAT PRF-911  
CONCENTRIC RING (CAL  
DATE 2-2023)
- ALL STANDARDS ON 1  
YEAR CAL CYCLE.

TABLE 1: SURFACE RESISTANCE DATA

Test Method	Surface Resistance (Ohms) @ 12.8% RH, 23.2°C, 62 hours conditioning								
	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Min	Max	Mean
ANSI/ESD STM 11.11	$6.8 \times 10^3$	$7.2 \times 10^3$	$6.8 \times 10^3$	$7.1 \times 10^3$	$7.4 \times 10^3$	$6.5 \times 10^3$	$6.5 \times 10^3$	$7.4 \times 10^3$	$6.97 \times 10^3$

Test Method	Surface Resistance (Ohms) @ 50.3% RH, 23.3°C, 55 hours conditioning								
	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Min	Max	Mean
ANSI/ESD STM 11.11	$1.9 \times 10^3$	$4.9 \times 10^3$	$4.6 \times 10^3$	$3.7 \times 10^3$	$4.7 \times 10^3$	$5.3 \times 10^3$	$1.9 \times 10^3$	$5.3 \times 10^3$	$4.18 \times 10^3$

**TABLE 2: VOLUME RESISTANCE DATA**

Test Method	Volume Resistance (Ohms) @ 12.8% RH, 23.2°C, 62 hours conditioning								
	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Min	Max	Mean
ANSI/ESD STM 11.12	$7.3 \times 10^3$	$6.9 \times 10^3$	$7.4 \times 10^3$	$7.1 \times 10^3$	$6.3 \times 10^3$	$6.4 \times 10^3$	$6.3 \times 10^3$	$7.4 \times 10^3$	$6.90 \times 10^3$

Test Method	Volume Resistance (Ohms) @ 50.3% RH, 23.3°C, 55 hours conditioning								
	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Min	Max	Mean
ANSI/ESD STM 11.12	$3.5 \times 10^3$	$4.9 \times 10^3$	$3.4 \times 10^3$	$2.6 \times 10^3$	$4.3 \times 10^3$	$3.4 \times 10^3$	$2.6 \times 10^3$	$4.9 \times 10^3$	$3.68 \times 10^3$